



Abrasives, Electro Minerals & Metals

TECHNICAL DATA

Brand Name: **Commercial Steel Shot** Mac'Ants Group Ref: **SS**

Product: Standard Steel Shot

Description: A high standard roundness steel shot media.

Application: Steel Shot gives a hammered or peened effect for use on ferrous castings and fabrications. Particularly used in airless automated equipment where its long life is efficient. The special hardened SS-M & SS-X should only be used in air driven systems.

Chemical Composition:

Compound	Chemical Formula	Typical Content %
Carbon	C	0.85 – 1.2
Silicon	Si	0.4 - 1.5
Sulphur	S	0.05
Phosphorus	Ph	0.05
Manganese	Mn	0.35 – 1.2

Physical Parameters:

Bulk Density	+4.6 g /cc
Shape	Shot - Spherical
Colour	Blue Grey
Specific Gravity	NA
Hardness	SS: 45 - 52 HRC

Gradation:

GRADE	SS780	SS660	SS550	SS460	SS390	SS330
Product Size (mm)	2.00 - 2.80	1.70 - 2.40	1.40 - 2.00	1.20 - 1.70	1.00 - 1.40	0.85 - 1.20
GRADE	SS280	SS230	SS170	SS110	SS70	
Product Size (mm)	0.71 - 1.0	0.60 - 0.85	0.42 - 0.71	0.30 - 0.50	0.18 - 0.35	

Minimum percentage of media between sizes shown varies from 60% to 100% subject to particular grade, further details on request.

Packaging:

Typically 25 kg woven polypropylene sacks, but 1000kg big bags are available and custom label on application

Page: 1-3-2
Issue: 3
Date: Dec 2011

Document Status: **Controlled / Uncontrolled**

E & OE

Mac'Ants Group, Todwick Road, Dinnington, Sheffield S25 3SE UK
Tel: +44 (0) 1909 552500 Fax: +44 (0) 1909 568726
Email: group@macants.co.uk www.macants.co.uk